

Aramid Camouflage	
Nominal Weight	5.4 osy (183 gsm)
Tear Strength ASTM D 3787 (w x f, lbs)	8.5 x 5.5
Breaking Strength (w x f, lbs)	185 x 130
Flame Resistance (w x f, lbs) ASTM D 6413 (AATCC 135,3,V,Aiii)	
Before Laundering After Flame (sec) 0 x 0 After Glow (sec) 1 x 1 Char Length (in) 2.5 x 2.5 Melt/Drip None	
After Laundering, 5 cycles After Flame (sec) 0 x 0 After Glow (sec) 1 x 1 Char Length (in) 2.5 x 2.5 Melt/Drip None	
Fabric Break Open (sec) (GL-PD-10-13)	>30
Dimensional Stability (w x f, % change) AATCC 96, Test: VIc After Laundering, 5 cycles	-3.1 x -7.5
Air Permeability (ft.³/min./ft.²) ASTM D 737	80