

	SL2I
Nominal Weight	7.5 osy (254 gsm)
Quilt Thread	Aramid
Made in America	Yes
Heat Resistance NFPA 1971 - 2013	Pass
TPP TPP with Advance™, Crosstech® Type 2c NFPA 1971 - 2013	37 - 39
Vertical Flammability ASTM 5034	
char length	<1.0 in
char length after 5 launderings after flame	<1.0 in 0
Thermal Shrinkage NPFA 1971-2007	
500°F at 5 minutes after 5 launderings	-5 x -0.5% -6.0 x -0.5%
Trapezoidal Tear Strength ASTM D 5587	
initial	25 x 100 lbs
after 5 launderings	25 x 95 lbs
Laundry Shrinkage AATCC 135	
after 5 launderings	<5.0 x <5.0%