

Nominal Weight	7.5 osy (235 gsm)		
Fabric Content	PBI® / DuPont™ Kevlar®		
Weave	Modified Plain		
Colors	Natural Gold / Black		
Finish	Super Shelltite™		
Made in America	Yes		
Certifications	NFPA 1971		
Taber Abrasion	4,000 cycles		
TPP UL Certified results with Gore® CROSSTECH® Black moisture barrier	NFPA 1971	THL UL Certified results with Gore® CROSSTECH® Black moisture barrier	NFPA 1971
Quantum4™	41 - 43	Quantum4™	240 - 260
Quantum3D® SL2	45 - 47	Quantum3D® SL2	225 - 245
Defender® M SL2	42 - 44	Defender® M SL2	245 - 265
Caldura® SL2	40 - 42	Caldura® SL2	235 - 255
Trap Tear	Natural		Black
initial	55 x 55 lbf (245 x 245 N)		46 x 44 lbf (205 x 196 N)
5x after wash	55 x 55 lbf (245 x 245 N)		42 x 41 lbf (187 x 182 N)
Tensile Strength	Natural		Black
initial	300 x 300 lbf		270 x 260 lbf
10x after wash	280 x 280 lbf		250 x 260 lbf
Flame Resistance			
initial char length	0.6 x 0.6 in		
5x after wash	0.4 in x 0.4 in		
after flame	0 sec		
Thermal Shrinkage			
initial	< 2.0%		
5x after wash	< 3.0%		
Water Absorption			
initial	< 2.0%		
5x after wash	< 5.0%		