

<b>Nominal Weight</b>	6.6 osy (225 gsm)		
<b>Special Feature</b>	Tencate ENFORCE™ Technology (Patent Pending)		
<b>Fiber Blend</b>	DuPont™ Nomex®, DuPont™ Kevlar®		
<b>Weave</b>	Twill		
<b>Colors</b>	Khaki, Light Gold, Dark Gold, Black, Yellow, Spruce Green		
<b>Finish</b>	Super Shelltite™		
<b>Made in America</b>	Yes		
<b>Certifications</b>	NFPA 1971 / NFPA 1951 (Rescue & Recovery)		
<b>Taber Abrasion</b> ASTM 03384	3,000 cycles		
<b>TPP</b> UL Certified results using Gore® CROSSTECH® Black moisture barrier	<b>NFPA 1971</b>	<b>THL</b> UL Certified results using Gore® CROSSTECH® Black moisture barrier	<b>NFPA 1971</b>
Quantum3D® SL2	41 - 43	Quantum3D® SL2	250 - 270
Caldura® SL2	40 - 42	Caldura® SL2	270 - 290
Defender® M SL2	44 - 46	Defender® M SL2	220 - 240
<b>Trap Tear</b>	ASTM 5587, NFPA 1971 (WARP X FILL)		
initial	45 x 45 lbf (200 x 200 N)		
5x after wash	45 x 45 lbf (200 x 200 N)		
<b>Tensile Strength</b>	ASTM m5034 (WARP X FILL)		
initial	350 x 350 lbf (1,555 x 1,555 N)		
10x after wash	350 x 350 lbf (1,555 x 1,555 N)		
<b>Flame Resistance</b>	ASTM D6413, NFPA 1971, CHAR LENGTH (WARP X FILL)		
initial char length	0.5 in x 0.5 in (15 x 20mm)		
5x after wash	0.4 in x 0.4 in (15 x 20mm)		
after flame	0 sec		
<b>Thermal Shrinkage</b>	NFPA 1971-2013		
initial	<1.0%		
5x after wash	<1.0%		
<b>Water Absorption</b>	AATCC 42		
initial	<5.0%		
5x after wash	<7.0%		