

STYLE 469™

Nominal Weight	7.5 osy (255 gsm)
Weave	Twill
Fiber Blend	Nomex®, Kevlar® / P-140
Finish	Wickwell Plus
Made in America	Yes
Flame Resistance	
after flame	0 sec
after glow	3.0 x 3.0 sec
char length	2 x 2 in (5.1 x 5.1 cm)
RPP Rating	
initial	9.7 cal/cm ²
after 5 launderings	9.54 cal/cm ²
Thermal Shrinkage	-1.5% x -1.5%
Total Heat Loss	512.3 W/m ²
Breaking Strength	275 x 240 lbf 1225 x 1070 N
Tearing Strength	20 x 20 lbf 90 x 90 N
Dimensional Stability	
warp	<4in%
fill	<2in%
Air Permeability	55 ft ³ /ft ² /min



All listed data represent typical values. Results from multiple tests unless otherwise stated. To the best of our knowledge, all information contained herein is accurate. TenCate Protective Fabrics USA assumes no liability whatsoever for the accuracy or completeness of the information contained herein. Users of any substance must satisfy themselves by independent investigation that the material can be used safely. TenCate Protective Fabrics describes only certain hazards but cannot guarantee these are the only hazards. Copyright © 2017 TenCate Protective Fabrics USA. STYLE469™ is a trademark of TenCate Protective Fabrics USA. TSTC.pdf | Version 12302016A

6501 Mall Boulevard, Union City, GA 30291 | USA +1 (770) 969-1000 | TenCateFabrics.com