TECASAFE®PLUS TechT4™



BASE LAYER FR PROTECTION

TechT4™ feels just like a t-shirt while offering lightweight, comfortable FR protection where you need it most – next to skin.

COOL, DRY AND COMFORTABLE

Integrated wicking COOLDERM™ TECHNOLOGY offers enhanced moisture management to promote body temperature regulation and breathability.

A MULTI-LAYERED APPROACH

The base component of the multi-layer FR system, Tech $T4^{TM}$ offers comfort with no-melt / no-drip next-to-skin protection.





TECHNICAL DATA*			TECASAFE®PLUS TECHT4™		
Nominal Weight			5.0 osy (170 gsm)		
Construction			Jersey		
Color			Navy, Midnight Navy, Sand, Black, Gray		
Fiber Content			Lyocell, Modacrylic, Nylon		
Certification(s)			ASTM 1506		
Thermal Testing (Flame Resis	stance)				
Energy Breakopen Threshold NFPA 70E, ASTM 1959	EBT Rating		4.8 cal/cm ²		
	PPE Category		Category 1		
Vertical Flame ASTM 6413, NFPA 2112	Initial	After flame	< 2.0 sec		
		Char length	< 6.0 in (150 mm)		
Physical Testing					
Burst Strength – Ball Method ASTM D3787			70 lbf (310 N)		
Burst Strength – Mullen Method ASTM D3786			65 psi (460 kPa)		
Dimensional Stability AATCC 135			< 10 %		
Fabric Stretch and Recovery	Fabric Stretch		24 % x 43 %		
	Fabric Recovery		92.5 % x 87 %		
Comfort					
Air Permeability ASTM D737			325 ft³/ft²/min		
Appearance *Score 5 (best) to 1 (Wor	rst)				
Color Fastness Laundering	Shade Change (AATCC 612A)		Up to 4 *		
Xenon Light Exposure AATCC 16	After 20 Hours		Up to 3-4 *		
Pilling Resistance ASTM D3512	Initial: 60 min		Up to 4-5 *		

^{*} All values subject to final certification and specification. Tested on specific colors. Appearance is dependent on shade of fabric.

AVAILABLE CO	LORS	OPTIONAL COLORS			
Navy	Midnight Navy	Sand	Black	Gray	Additional color options may be available. Please contact TenCate Protective Fabrics for more information.
					Color shades and textures may vary. Please contact your sales representative for swatch samples.







All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.