TECASAFE® ONE



EXCEPTIONAL VALUE

At 5.7-ounces, this durable, inherently flame-resistant fabric offers premium benefits at a competitive price point.

ULTRA BREATHABLE

A lightweight, comfortable feel that's ~5x more breathable so wearers can stay cool and dry in harsh conditions.

WASH AFTER WASH

Tecasafe® One boasts outstanding color retention — even through heavy wear and industrial laundering.

TECASAFE®ONE

TECHNICAL DATA*			TECASAFE®ONE		
Nominal Weight			5.7 osy (193 gsm)		
Construction			Woven		
Color			Denim Navy, Gray, Hi-Vis Yellow, Khaki, Light Blue, Light Gray, Orange, Red, Royal, Spruce, Yellow		
Fiber Content			Modacrylic, Lyocell, Aramid		
Certification(s)			ASTM 1506, NFPA 2112, NFPA 70E, ANSI 107, CAN/CGSB155.20, NFPA 1977		
Thermal Testing (Flame Resi	stance)				
Manikin Burn NFPA 2112	Predicted Body Burn		19.67 %		
Arc Thermal Protective Rating (ATPV)NFPA 70E, ASTM 1959	ATPV Rating		8.2 cal/cm ²		
	PPE Category		Category 2		
Vertical Flame	Initial and 100x after wash	After flame	< 2.0 sec		
ASTM 6413, NFPA 2112		Char length	< 4.0 in (100 mm)		
Thermal Shrinkage NFPA 2112	Initial and 3x after wash		< 10 %		
Physical Testing					
Tensile Strength ASTM D5043	Initial (warp x fill)		110 x 75 lbf (490 x 334 N)		
Elmendorf Tear ASTM D1424	Initial (warp x fill)		8.0 × 7.0 lbf (36 × 31 N)		
Dimensional Stability AATCC 135			< 4.0 %		
Seam Strength ASTM D434, Force at 0.25 in slippage			30 lbf (134 N)		
Comfort					
Air Permeability ASTM D737			135 ft³/min/ft²		
MVTR ASTM E96			1600 g/m²/24h		
Appearance *Score 5 (best) to 1 (W	orst)				
	Laundering AATCC 61 2A	Shade Change	Up to 4 *		
Color Fastness	Xenon Light Exposure	After 20 Hours	Up to 2-3 *		

^{*} All values subject to final certification and specification. Tested on specific colors. Appearance is dependent on shade of fabric.

AVAILABLE (COLORS	OPTIONAL COLORS				
Light Blue	Denim Navy	Royal	Spruce	Gray	Light Gray	Additional color options may be available. Please contact TenCate Protective Fabrics for more information.
Hi-Vis Yellow	Yellow	Orange	Red	Khaki		Color shades and textures may vary. Please contact your sales representative for swatch samples.

Initial: 60 min





Exposure AATCC 16

Pilling Resistance ASTM D3512



Up to 4.5 *

